

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Amendments To The Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A process for manufacturing an absorbent dryformed paper web having a plurality of layers, with at least one center layer containing a superabsorbent material comprising:

laying a web of cellulose fibers, admixed with thermobonding fibers, onto a forming wire, wherein the thermobonding fibers comprise about 3 - 25 wt% of the total fiber content;

applying a binder, wherein the amount of dry matter in the binder is from about 0.5 - 15 wt% and the amount of dry matter applied to the surface of the web is from about 0.5 - 20 g. of dry matter per square meter of web surface; and

heating the web to a temperature sufficient to melt the thermobonding fibers and increase the tensile strength of the finished product.

2. (Previously Presented) The process according to claim 1 wherein the amount of dry matter in the binder is from about 0.5 - 15 wt%.

3. (Original) The process according to claim 1 wherein the binder is applied in an amount of about 0.5 - 10 grams dry matter per square meter of web surface.

4. (Original) The process according to claim 1 wherein the binder is an aqueous binder.

Claims 5-6. (Cancelled)

7. (Original) The process according to claim 1 wherein the binder contains pigments admixed therewith.

8. (Previously Presented) The process according to claim 2 wherein said web comprises about 10 - 25 wt% thermobonding fibers and the amount of binder applied to the surface of the web is about 0.5 - 10 grams per square meter of web surface.

9. (Previously Presented) The process according to claim 2 wherein said web comprises about 3 - 7 wt% of thermobonding fibers and the amount of binder applied to the surface of the web is about 5 - 20 grams per square meter of web surface.

10. (Withdrawn) An apparatus for preparing a dryformed absorbent web comprising:

a device for drylaying fibers onto a forming wire for forming a fibrous web, wherein the device for drylaying

operates based upon a mixture of cellulose fibers admixed with thermobonding fibers;

heating means defining a heating zone for bonding the web fibers;

a station for applying binder to at least one surface of the web, said binder being applied in amounts so as to render the finished web substantially non-linting.

11. (Withdrawn) An apparatus according to claim 10 wherein the binder is applied to at least one surface of the web in an amount corresponding to 0.5 - 10 grams of dry matter per square meter of web surface.

12. (Withdrawn) The apparatus according to claim 10 wherein the station for applying binder to the surfaces of the web is a foulard for applying the binder in an aqueous foam carrier.

13. (Withdrawn) An absorbent dryformed paper web material predominantly comprising cellulose fibers and prepared so as to exhibit bonding of the fibers therein, wherein said bonding results from a combination of:

thermobonding fibers distributed evenly throughout the thickness of the web; and

a surface disposition of a binding agent in an amount of about 0.5 - 20 grams per square meter of web on at a least one side of the web.

14. (Withdrawn) The web material according to claim 13, wherein the thermobonding fibers are distributed evenly throughout the thickness of the web.

15. (Withdrawn) The web material according to claim 13, wherein the binding agent is applied to at a least one surface of the web in an amount of about 3 - 6 grams per square meter of web.

16. (Withdrawn) The web material according to claim 13 wherein the web comprises a mixture of about 75 - 95 % cellulose fibers and about 10 - 25 % thermobonding fibers, the binding agent being present in an amount of about 0.5 to 10 grams per square meter of web surface.

17. (Withdrawn) The web material according to claim 13 wherein the web material comprises a mixture of about 93 - 97% cellulose fibers and about 3 - 7% thermobonding fibers, the binding agent being present in an amount of about 0.5 - 20 grams per square meter of web surface.

18. (Withdrawn) The web material according to claim 13 wherein the binding agent is present in an amount of about 1 - 5 grams per square meter of web surface.

19. (Withdrawn) A composite product wherein the outer layer of said laminated product is the web material of claim 13.

20. (Withdrawn) The composite product according to claim 18 wherein the binding agent is the dry product of an aqueous binder dispersion.

21. (Withdrawn) The laminated product according to claim 19 wherein another layer of the product is comprised of a superabsorbent material.

22. (Withdrawn) The web material according to claim 13 wherein the binding agent is pigmented.